

Technical Information

TINGOLEN 5230 K

Modifier for polyurethane formulations

Density	(20°C)	DIN 51757	g/cm ³	0,889 – 0,905
Viscosity	(20°C)	DIN 53015	mPas	6 - 10
Refractive index	(20°C)	DIN 51423, T2		1,505 – 1,526
Colour Gardner		DIN ISO4630		≤ 5
Colour				yellow
Content of water		DIN 51 777	%	≤ 0,03

Applications:

Non-hazardous/non-classified modifier for polyurethane formulations

Thinner

Viscosity modifier

Hydrophobic modifier

Non-reactive with polyurethane (isocyanate)

12.01.2016