

Technical Information



Tingolen 59 K

Modifier for polyurethane formulations

Density	(20°C)	DIN 51757	g/cm ³	0,92
Viscosity	(20°C)	DIN 53015	mPas	10 -25
Refractive index	(20°C)	DIN 51423, T2		1,54
Colour Gardner		DIN ISO4630		≤ 8
Colour				yellow
Content of water		DIN 51 777	%	≤ 0,03

Applications:

Non-hazardous/non-classified modifier for polyurethane formulations

Thinner

Viscosity modifier

Hydrophobic modifier

Non-reactive with polyurethane (isocyanate)

01.05.2015

TRG Cyclamin GmbH BU TINGO
Hohendorfer Str. 20
D-39218 Schönebeck
Germany

Telephone: +49 (0) 3928 787080
Fax: +49 (0) 3928 787088
E-mail: trg@trg-cyclamin.de
Homepage: www.tingo.de