

Technical Information

Tingolen C1/ 5-10

Modifier for polyurethane formulations

Density	(20°C)	DIN 51757	g/cm ³	0,897 – 0,910
Viscosity	(20°C)	DIN 53015	mPas	5 – 10
Refractive index	(20°C)	DIN 51423, T2		1,518 – 1,533
Colour (Gardner)		DIN ISO4630		1
Colour (APHA)		DIN ISO 6271-2		<30
Content of water		DIN 51 777	%	≤ 0,03

Applications:

Non-hazardous/non-classified modifier for polyurethane formulations

Thinner

Viscosity modifier

Hydrophobic modifier

Non-reactive with polyurethane (isocyanate)

20.11.2017